

Dimension Plank

| | |
|-------------------|------------------|
| DIMENSIONS | 1900 mm x 190 mm |
| THICKNESS | 15 mm |
| TOP LAYER | 4.00 mm |

Dimension Pack

| | |
|---------------------------|----------------------|
| PACK LENGTH | 1920 mm |
| PACK WIDTH | 198 mm |
| PACK THICKNESS | 130 mm |
| PACK WEIGHT | 25.70 kg |
| PLANKS / PACK | 8 |
| M²/PACK | 2.888 m ² |

Dimension Pallet

| | |
|-----------------------------|-----------------------|
| PALLET LENGTH | 1950mm |
| PALLET WIDTH | 1000 mm |
| PALLET HEIGHT | 1145 mm |
| PALLET WEIGHT | 1140,00kg |
| PACKS / PALLET | 40 |
| M²/PALLET | 115.52 m ² |



Features


Top layer

| | |
|-----------------------|--|
| WOOD SPECIES | Oak |
| LATIN NAME | Quercus Mongolica |
| CATEGORY | CLASSIC: A rustic floor with knots and slight variations in color, no core defects and occasional traces of sapwood. |
| CONSTRUCTION | multi-ply or 3 layers solid |
| THICKNESS | 4,00 mm |
| STRIPS | 1 |
| CUTTING METHOD | Sawn veneer |
| BEVEL | 4 sides (0.5 mm) |
| FINISHING | Smoked , Hardwax oil or UV lacquered |
| SURFACE | Brushed or hand scraped |

Composition of frame

| | |
|---------------------------------|----------------------|
| TYPE | Eucalyptus framework |
| WOOD TYPE BASIS | Eucalyptus & Poplar |
| CONSTRUCTION BASIS | 7-9 layers cross lay |
| TOTAL THICKNESS OF FRAME | 11mm |
| ADHESIVE | Dynea |

Steps

| | | |
|---|---|---|
| SYSTEM | APPLICATION | UNDERFLOOR HEATING |
| Tongue and groove system  | Light household use Normal household use Moderate commercial use Normal commercial use Intensive commercial use | Yes RE-SANDABLE Yes |
| | | More info on www.styletimberfloor.com.au "Euro oak Milano collection " |

Certification This product conforms to CE standard EN 14342:2005 + A1: 2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and Multilayer parquet elements)

| Assessed property | Classification or test method | Requirement | Result or classification | Evaluation |
|-----------------------------------|-------------------------------|--------------------------------------|-----------------------------|--------------|
| Release of formaldehyde | EN 717-1 | $\leq 0.124 \text{ mg/m}^3$ | $\leq 0.014 \text{ mg/m}^3$ | E0 |
| Width-permit deviation | EN 13647 | $\pm 0.2 \text{ mm}$ | -0.1mm | Fulfil |
| Moisture content | EN 13183-1 | $9 \pm 2\%$ | 7.0% | Fulfil |
| Reaction to fire (floor) | AS ISO 9239.1-2003 | $\text{CRF} \geq 4.5 \text{ KW/m}^2$ | 6.9 KW/m ² | Fulfil |
| Reaction to fire (wall & ceiling) | AS/NZS 3837:1998 | Group number 1-4 | Group number 3 | Middle range |
| Sliptest-Wet Pendulum | AS 4586&4663 (2013) | P1-P5 | P2 | Middle range |
| Hardness | Janka Rating | None | 1360 | Middle range |

Technical Specifications

- Additional tests:

- Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)

- The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)